

## Product: igutek P360

### General Properties:

density:	1.24 g/cm <sup>3</sup>
colour:	light beige
saturation with moisture absorption at 23°C / 50% r. h.:	0.5 weight %
saturation with water:	2.1 weight %

### Mechanical Properties:

flexural modulus:	1300 MPa
flexural strength:	50 MPa

### Thermal Properties:

highest long term service temperature <sup>1)</sup> :	110°C
highest short term service temperature <sup>1), 2)</sup> :	130°C
lowest service temperature:	-30°C

### Electrical Properties:

surface resistivity:	>10 <sup>12</sup> Ω
----------------------	---------------------

<sup>1)</sup> relaxation possible

<sup>2)</sup> without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.